



The Liner Company

SOLUTIONS

ENVIRONMENTAL PROTECTION, INC.

9939 US-131 South NE
Mancelona, Michigan
49659

800-OK-LINER
Phone | 231-587-9108
Fax | 231-587-8020

www.geomembrane.com

TYPICAL APPLICATIONS


Lagoons

Ponds

Floating covers and similar containment's

Potable water containment's

Hydroponic farming applications



Reinforced polypropylene provides a versatile flexible geomembrane liner. The unique three ply construction with a combination of custom fabric reinforcement encapsulated by extruded high performance polypropylene provides a strong, highly chemical resistant liner.

The chemically inert polymer is modified to provide many specialized properties that include excellent flexibility, low thermal coefficient of expansion and contraction, outstanding dimensional stability, wide temperature range for excellent seaming and good chemical resistance in exposed liner applications. All factory and field seams are thermally welded.

Gauge, Nominal (mils) Plies Reinforcing	ASTM-D751	36 ±10% 1
Breaking Strength	ASTM-D751, Method A	250 x 200 lbs.
Tear Strength (lbs. Min.)	ASTM-D751, Tongue Tear	100 lbs.
Low Temperature (°F)	ASTM-D2136, 1/8" Mandrel – 4 hrs.	-65°F
Dimensional Stability (% Change Max.)	ASTM-D1204 (180°F/1 hour)	1 %
Hydrostatic Resistance (psi Min.)	ASTM-D751, Method A	350 psi
Ply Adhesion (lbs./in. Min.)	ASTM-D413	20 lbs.
Puncture Resistance	FTM-101 B, Method 2031	250 lbs.
Water Absorption (Max. % Weight Change)	ASTM-D471	<1%
U. V. Resistance (Hours)	ASTM G-26 Xenon Arc @ 80°C	Pass @ 12,000 hours +
Resistance to Soil Burial (% Tensile Retention)	ASTM-D3083 (Part. 9.5)	90% Min.

Preserving water resources for future generations

Visit our Internet web site at
www.geomembrane.com