SOLUTIONS



30 Mil Dimpled Textured Polyethylene SPECIFICATIONS

TYPICAL APPLICATIONS:Temporary Covers · Pond Liners · Coal Mining · Exposed Applications
Exposed Applications · Oil and Gas · Modular Tank Liners
Landfill Caps · Waste Disposal Liners · Canal Liners · Fish Farm Applications

Textured Scrim Reinforced Polyethylene provides design engineers with new solutions for the most challenging projects. The texture provides increased friction between various soil and geosynthetic layers allowing for steeper slope designs. This is ideal for applications requiring exceptional slope stability such as landfill caps, mining leach pads and containment ponds.

30DT1 is linear a low density polyethylene geomembrane reinforced with a heavy encapsulated 1300 Denier polyester reinforcement. In addition to excellent dimensional stability the tri-directional reinforcement provides exceptional tear and tensile strength. This membrane is formulated with thermal and UV stabilizers to assure a long service life..

All factory and field seams are thermally welded.

| Material: Thickness ±10% | ASTM D-5199 | .030" | Asperity Height | | 24 Mil |
|------------------------------------|-------------|-------------|--|----------------------|---------------|
| Weight | ASTM D-5261 | 125 lbs/msr | Construction Extrusion | laminated with scrim | reinforcement |
| Wolgin | | | Water Absorption (max % weight change) | ASTM D-471 | <1% |
| Grab Tensile Strength | ASTM D-7004 | 150 lbs | UV Resistance (Xenon Arc, 15,120 kj/m ² | ASTM G-155 | PASS |
| Grab Tensile Elongation | ASTM D-7003 | 50 % | total radiant exposure) | | |
| Tongue Tear | ASTM D-5884 | 50 lbs | Factory Fabricated Seams Peel Strength (lbs/in, min) | S: ASTM D-7747(A) | 20 |
| CBR Puncture Resistance | ASTM D-6241 | 375 lbs | Shear Strength (Ibs/in, min) | ASTM D-7747(B) | 200 |

These data are based on tests believed to be reliable. However, these are laboratory tests that may not simulate actual use conditions. They are provided for your informational purposes only. No warranty, express or implied, including any other further warranty of fitness for a particular purpose or merchantability, is made by this promotional literature.

geomembrane.com